



Mechanical Rubber

PRODUCTS COMPANY, INC.

PO Box 593 • 77 Forester Ave., Suite 1, Warwick, NY 10990-1107 • 845-986-2271 • Fax 845-986-0399 • www.mechanicalrubber.com

Technical Data Sheet

TYPICAL PROPERTIES OF MR35-241A-BK-09

SPECIFICATIONS:

ASTM D6576, TYPE 2, GRADES A / B, SOFT
ASTM D1056, 2C1
SAE J18, 2C1
MILR6130, TYPE 2, GRADE C
CONDITION SOFT

GENERAL PROPERTIES:

CLOSED CELL NEOPRENE SPONGE

TEMPERATURE RANGE:

-40°F TO 200°F

COLOR:

BLACK

TYPICAL RESISTANCES:

ACID
ALKALI
KETONES
OXIDATION
OZONE

PROCESSES:

DIE CUTTING
SHEETING
FABRICATION

APPROVALS:

FMVSS-302: FLAME

PHYSICAL PROPERTIES		
PHYSICAL PROPERTY	TEST METHOD	TYPICAL RESULT
DENSITY - DUROMETER	ASTM D1056, ASTM D2240	7 - 11 PCF 50±5, SHORE OO
TENSILE STRENGTH	ASTM D412	80 PSI
ELONGATION	ASTM D412	150%
TEAR RESISTANCE	ASTM D624	14 LB/IN
COMPRESSION SET	ASTM D395 METHOD B ASTM D1056	< 25%
COMPRESSION DEFLECTION	ASTM D575, ASTM D1056	2 - 5 PSI
ACCELERATED HEAT AGING	ASTM D573, ASTM D1056	±30%
WATER ABSORPTION	ASTM D1056	< 5%
OIL RESISTANCE	ASTM D471	N/A
LOW TEMPERATURE	ASTM D1056, ASTM D2137 METHOD A	N/A

The above information is furnished as a guide for selecting materials. Mechanical Rubber disclaims liability for results or use of this information. It is the end user's responsibility to obtain and test samples when determining suitability of material for a particular application.

