



# Mechanical Rubber

## PRODUCTS COMPANY, INC.

PO Box 593 • 77 Forester Ave., Suite 1, Warwick, NY 10990-1107 • 845-986-2271 • Fax 845-986-0399 • www.mechanicalrubber.com

### Technical Data Sheet

### TYPICAL PROPERTIES OF MR35-242A-BK-03

**SPECIFICATIONS:**

ASTM D6576, TYPE 2, GRADES A, B, & C, MEDIUM  
 ASTM D1056, SCE42  
 ASTM D1056, RE42  
 ASTM D1056, 2A2  
 MILR6130, TYPE 2, GRADE A, B, & C CONDITION MEDIUM  
 MILC3133 / MILSTD670B, SCE7

**GENERAL PROPERTIES:**

CLOSED CELL SPONGE  
 NEOPRENE/EPDM/SBR BLEND

**TEMPERATURE RANGE:**

-40°F TO 200°F

**COLOR:**

BLACK

**TYPICAL RESISTANCES:**

ACID  
 ALKALI  
 KETONES  
 OXIDATION  
 OZONE

**PROCESSES:**

DIE CUTTING  
 SHEETING  
 FABRICATION

**APPROVALS:**

UL 94 HF-1: FLAME  
 SAE J369: FLAME  
 FMVSS-302: FLAME

PHYSICAL PROPERTIES		
PHYSICAL PROPERTY	TEST METHOD	TYPICAL RESULT
DENSITY - DUROMETER	ASTM D1056, ASTM D2240	4 - 8 PCF 50±5, SHORE OO
TENSILE STRENGTH	ASTM D412	100 PSI
ELONGATION	ASTM D412	125%
TEAR RESISTANCE	ASTM D624	9.6 LB/IN
COMPRESSION SET	ASTM D395 METHOD B ASTM D1056	< 35%
COMPRESSION DEFLECTION	ASTM D575, ASTM D1056	5 - 9 PSI
ACCELERATED HEAT AGING	ASTM D573, ASTM D1056	±30%
WATER ABSORPTION	ASTM D1056	< 10%
OIL RESISTANCE	ASTM D471	N/A
LOW TEMPERATURE	ASTM D1056, ASTM D2137 METHOD A	N/A

The above information is furnished as a guide for selecting materials. Mechanical Rubber disclaims liability for results or use of this information. It is the end user's responsibility to obtain and test samples when determining suitability of material for a particular application.

