



Mechanical Rubber

PRODUCTS COMPANY, INC.

PO Box 593 • 77 Forester Ave., Suite 1, Warwick, NY 10990-1107 • 845-986-2271 • Fax 845-986-0399 • www.mechanicalrubber.com

Technical Data Sheet

TYPICAL PROPERTIES OF MR60-243C-BK-09

SPECIFICATIONS:

AMS3195
R10470
MILR46089, GRADE MEDIUM

GENERAL PROPERTIES:

CLOSED CELL SILICONE SPONGE

TEMPERATURE RANGE:

-103°F TO 450°F

COLOR:

BLACK

TYPICAL RESISTANCES:

ABSORPTION - WATER
ACID - DILUTED
COLD
ELECTRICAL INSULATION
HEAT
HEAT AGING
OXIDATION
OZONE
REBOUND - COLD & HOT
SUNLIGHT AGING
WEATHER

PROCESSES:

DIE CUTTING
SHEETING
FABRICATION
EXTRUSION

APPROVALS:

PHYSICAL PROPERTIES		
PHYSICAL PROPERTY	TEST METHOD	TYPICAL RESULT
DENSITY - DUROMETER	ASTM D1056, ASTM D2240	9 PCF 70±10, SHORE OO
TENSILE STRENGTH	ASTM D412	100 PSI
ELONGATION	ASTM D412	200%
TEAR RESISTANCE	ASTM D624	N/A
COMPRESSION SET	ASTM D395 METHOD B ASTM D1056	60% MAX.
COMPRESSION DEFLECTION	ASTM D575, ASTM D1056	11 PSI
ACCELERATED HEAT AGING	ASTM D573, ASTM D1056	-5 TO 30%
WATER ABSORPTION	ASTM D1056	5% MAX.
OIL RESISTANCE	ASTM D471	AS TESTED
LOW TEMPERATURE	ASTM D1056, ASTM D2137 METHOD A	AS TESTED

The above information is furnished as a guide for selecting materials. Mechanical Rubber disclaims liability for results or use of this information. It is the end user's responsibility to obtain and test samples when determining suitability of material for a particular application.

